



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification: C25B 11/04	A1	(11) International Publication Number: WO 95/05499 (43) International Publication Date: 23 February 1995 (23.02.95)
(21) International Application Number: PCT/GB94/01718 (22) International Filing Date: 4 August 1994 (04.08.94) (30) Priority Data: 9316926.6 13 August 1993 (13.08.93) GB (71) Applicant (for all designated States except US): IMPERIAL CHEMICAL INDUSTRIES [GB/GB]; Imperial Chemical House, Millbank, London SW1P 3JF (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): HODGSON, David, Ronald [GB/GB]; 7 Grenaby Avenue, Hinelley Green, Wigan, Merseyside WN2 4HZ (GB). (74) Agents: THOMAS, Ieuan et al.; ICI Chemicals & Polymers Ltd., Intellectual Property Dept., P.O. Box 11, The Heath, Runcorn, Cheshire WA7 4QE (GB).	(81) Designated States: AU, BR, CA, CN, CZ, FI, HU, JP, KR, NO, NZ, PL, RO, RU, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(54) Title: ELECTRODE AND PREPARATION THEREOF (57) Abstract <p>Preparation of an electrode comprising a substrate of a valve metal or of an alloy thereof having similar properties thereto and a coating thereon comprising at least an outer layer of an electrocatalytically-active material which comprises an oxide of at least ruthenium and an oxide of at least one non-noble metal by a one-step coating process which comprises the vapour phase deposition of a mixture of at least ruthenium and/or oxide thereof and at least one non-noble metal or oxide thereof onto the substrate. The outer layer is of substantially uniform thickness, the contours thereof are at least substantially the same as the contours of the substrate underlying it and the electrode affords an increased surface area for a given mass of catalyst and a more efficient use of catalyst to obtain a given thickness thereof.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

ELECTRODE AND PREPARATION THEREOF

This invention relates to an electrode for use in an electrolytic cell, particularly to an electrode for use as an anode in an electrolytic cell, especially in an electrolytic cell in which in operation chlorine is evolved at the anode, although use of the anode of the invention is not restricted to electrolyses in which chlorine is evolved, and to a method
5 for the preparation of the electrode.

Electrolytic processes are practised on a large scale throughout the world. For example, there are many industrial processes in which water or an aqueous solution is electrolysed, for example, an aqueous solution of an acid or an aqueous solution of an
10 alkali metal chloride. Aqueous acidic solutions are electrolysed in, for example, electrowinning, electroplating and electrorefining processes, and aqueous alkali metal chloride solutions are electrolysed in the production of chlorine and alkali-metal hydroxide, alkali metal hypochlorite, and alkali metal chlorate. The production of chlorine and alkali metal hydroxide is practised in electrolytic cells which comprise a mercury
15 cathode or in electrolytic cells which comprise a plurality of alternating anodes and cathodes, which are generally of foraminant structure, arranged in separate anode and cathode compartments. These latter cells also comprise a separator, which may be a hydraulically permeable porous diaphragm or a substantially hydraulically impermeable ion-exchange membrane, positioned between adjacent anodes and cathodes thereby
20 separating the anode compartments from the cathode compartments, and the cells are also equipped with means for feeding electrolyte to the anode compartments and if necessary liquid to the cathode compartments, and with means for removing the products of electrolysis from these compartments. In a cell equipped with a porous diaphragm, aqueous alkali metal chloride solution is charged to the anode compartments of the cell, and chlorine is discharged from the anode compartments and hydrogen and cell liquor
25 containing alkali metal hydroxide are discharged from the cathode compartments of the cell. In a cell equipped with an ion-exchange membrane aqueous alkali metal chloride solution is charged to the anode compartments of the cell and water or dilute aqueous alkali metal hydroxide solution to the cathode compartments of the cell, and chlorine and
30 depleted aqueous alkali metal chloride solution are discharged from the anode compartments of the cell and hydrogen and alkali metal hydroxide are discharged from the cathode compartments of the cell.

Electrolytic cells are also used in the electrolysis of non-aqueous electrolytes and in electrosynthesis.

It is desirable to operate such electrolytic cells at as low a voltage as possible in order to consume as little electrical power as possible and in such a way that the component parts of the electrolytic cell are long lasting, ie the electrodes in the electrolytic cell should have a long lifetime.

In recent years anodes which have been used in such electrolytic processes have comprised a substrate of titanium or of an alloy of titanium possessing properties similar to those of titanium and a coating of an electrocatalytically-active material on the surface of the substrate. An uncoated titanium anode could not be used in such an electrolytic process as the surface of the titanium would oxidize when anodically polarized and the titanium would soon cease to function as an anode. The use of such a coating of electrocatalytically-active material is essential in order that the titanium shall continue to function as an anode. Examples of such electrocatalytically-active materials which have been used include metals of the platinum group, oxides of metals of the platinum group, mixtures of one or more such metals and one or more such oxides, and mixtures or solid solutions of one or more oxides of a platinum group metal and tin oxide or one or more oxides of a valve metal, that is one or more oxides of titanium, tantalum, zirconium, niobium, hafnium or tungsten.

Recently it has been suggested in EP 0,437,178 that anodes wherein the coating comprises mixed oxides of iridium, ruthenium and titanium having oxide molar ratios of Ti:(Ir + Ru) of less than 1:1 and of Ru:Ir of between 1.5:1 and 3:1 can be prepared from a certain acidic aqueous solution.

Likewise, it has been suggested in J 59,064788 that electrode coatings can be prepared by the deposition of certain coatings from organic solvents onto a substrate followed by heating the coated substrate in oxygen.

We have now found surprisingly that electrodes for use in electrolytic cells may be prepared by the physical vapour deposition of a mixture of powders of (i) ruthenium oxide, (ii) a non-noble metal oxide, eg tin oxide, or a valve metal oxide and preferably (iii) a noble metal oxide other than ruthenium oxide (hereinafter referred to for convenience as "second noble metal oxide"), onto a suitable substrate. This method has the advantage that it affords a single step coating process for the preparation of an

electrode. Moreover, the durability of the electrode may be improved by a subsequent heat treatment as is more fully described hereinafter.

The present invention provides a method for the preparation of an electrode which (a) comprises a substrate of a valve metal or alloy thereof and a coating on the substrate which comprises at least an outer layer having uniform thickness, particularly where prepared by RF sputtering, and of good electrocatalytic activity and (b) when used as an anode in a cell in which chlorine is evolved at an anode has an acceptable overvoltage and often, as is hereinafter more fully described, has high durability.

According to the present invention there is provided a method for the preparation of an electrode which comprises a substrate of a valve metal or of an alloy thereof and a coating thereon comprising at least an outer layer of an electrocatalytically-active material which comprises an intimate mixture of ruthenium oxide and at least one non-noble metal oxide which process comprises the step of depositing a mixture of the aforementioned oxides on the substrate by physical vapour deposition (PVD).

Preferably, mixture of oxides in the outer layer of the coating on the electrode prepared by the process according to the present invention contains an oxide of a second noble metal.

As examples of PVD may be mentioned inter alia radio frequency (RF) sputtering, sputter ion plating, arc evaporation, electron beam evaporation, dc magnetron, reactive PVD, etc or combinations thereof. It will be appreciated that where combinations of evaporation techniques are used in the same evaporation chamber in the PVD system separate targets may be used, eg a ruthenium target and a tin target instead of, or in addition to, a mixed ruthenium/tin target. By "target" we mean the material which is vapourised to produce a vapour for deposition on the substrate in the PVD system.

The substrate of the electrode comprises a valve metal or an alloy thereof. Suitable valve metals include titanium, zirconium, niobium, tantalum and tungsten, and alloys comprising one or more such valve metals and having properties similar to those of the valve metals. Titanium is a preferred valve metal as it is readily available and relatively inexpensive when compared with the other valve metals.

The substrate may consist essentially of a valve metal or alloy thereof, or it may comprise a core of another metal, eg steel or copper, and an outer surface of a valve metal or alloy thereof.

5 The oxide of the non-noble metal in the outer layer of the coating may be, for example, a valve metal as hereinbefore described, or cobalt or preferably tin.

The oxide of the at least one second noble metal, where present in the outer layer of the coating, may be, for example, an oxide of one or more of rhodium, osmium, platinum or preferably iridium.

10 The electrode prepared by the process according to the present invention when used as an anode in an electrolytic cell in which chlorine is evolved at the anode, has a low overvoltage acceptable in terms of chlorine evolution, ie less than 100mV at 3kA/m². Moreover, we have found surprisingly that where the oxidic component of the aforementioned outer layer provides more than 30 atomic % of all the components in the outer coating, as measured by X-ray absorption spectroscopy, the electrode has high
15 durability.

The possibility is not excluded of the coating of the electrode comprising one or more further layers intermediate the outer layer and the substrate, but it will be described hereinafter with reference to a coating which consists of only the aforementioned outer layer.

20 The layers in the coating are described as variously comprising an oxide of ruthenium and an oxide of at least one non-noble metal and preferably an oxide of at least one second noble metal. Although the various oxides in the layers may be present as oxides per se it is to be understood that the oxides may together form a solid solution in which the oxides are not present as such. For example, where a layer in the coating,
25 particularly the outer layer, comprises a second noble metal oxide, eg iridium oxide, the intimate mixture may be in the form of a solid solution of, for example, ruthenium dioxide, iridium oxide and tin dioxide or a solid solution of two of them mixed with the third. We do not exclude the possibility that a noble metal per se or an alloy thereof may be present in the coating.

30 In general the electrode will be used in the electrolysis of aqueous electrolytes and although the electrode of the invention is particularly suitable for use as an anode at which chlorine is evolved the electrode is not restricted to such use. It may, for example,

be used as an anode in the electrolysis of aqueous alkali metal chloride solution to produce alkali metal hypochlorite or alkali metal chlorate, or it may be used as an anode at which oxygen is evolved.

5 The over-voltage and useful working lifetime of the electrode prepared by the method according to the present invention is dependent at least to some extent on the ratio of the components in the coating on the electrode and on the thickness thereof. The coating will generally comprise at least 10 mole % in total of oxide of noble metal, ie ruthenium and the second noble metal, where present, and at least 20 mole % of oxide of non-noble metal.

10 In general the coating will be present at a loading of at least 5 g/m² of nominal electrode surface, preferably at least 10 g/m². In general it will not be necessary for the coating to be present at a loading of greater than 100 g/m², preferably not greater than 50 g/m². Typically, the thickness of the outer layer of the coating is between 1 and 10 μ .

15 In the method according to the present invention, the chamber in the PVD system is charged with oxygen or ozone and an inert gas, preferably argon.

Where the method according to the present invention is carried out in the reactive mode, ie the target in the PVD system is metallic, the ratio of oxygen:argon is greater than 2:1 by volume and preferably is at least 4:1 by volume.

20 The specific conditions used in the method according to the present invention may be found by the skilled man by simple experiment.

For example, the pressure in the deposition chamber may be in the range 10^{-2} to 10^{-10} atmospheres, particularly where the coating comprises a mixture of ruthenium oxide, iridium oxide and tin oxide.

25 We have found that the useful working life of the electrode prepared by the method according to the present invention may be increased by subjecting it to a treatment at high temperature of at least 400°C, typically about 500°C, for at least one hour.

30 Where the electrode of the present invention comprises an intermediate layer it may, for example, comprise RuO₂ and an oxide of at least one non-noble metal. The oxide of the non-noble metal in the intermediate layer may be, for example, titanium oxide, zirconium oxide, or tantalum pentoxide or oxide of another noble metal.

TABLE 2

Time on load (days)	Cell voltage (volts)
0	3.3
127	3.4

Measurements of RuO₂ content of the electrocatalytically-active coating by X-Ray fluorescence (XRF) analysis revealed low coating losses under the aforementioned operating conditions as shown in Table 3.

TABLE 3

Time on load (days)	Loading RuO ₂ (g/m ²)
0	10.63
373	10.14

Examples 4 - 5

These Examples illustrate electrodes prepared by the method according to the present invention using arc-evaporation.

Ruthenium and tin metal powders, in weight ratio 3:7, were mixed and hot-pressed to form a PVD target. The PVD target was disposed in an arc evaporation system and a mixture of oxygen and argon was passed through the system.

Material was evaporated from the target and deposited onto titanium substrates which had been etched by the procedure described in Example 1.

The conditions used in the arc evaporation system are shown in Table 4.

TABLE 4

Example	Arc Current (A)	Flow Rates (sccm)		Substrate Bias (Volts)	Chamber Pressure (mbar)
		O ₂	Ar		
4	35	80	10	-50	0.003
5	20	40	10	-50	0.003

The chlorine overpotential of the electrode of Example 4 was found to be 85mV at 3kAm⁻², measured by the so-called "current interrupt method" in which a constant current

was interrupted, the potential decay curve was displayed on an oscilloscope from which the overpotential could be read directly.

5

10

15

20

25

30

CLAIMS

1. A method for the preparation of an electrode comprising a substrate of a valve metal or of an alloy thereof and a coating thereon comprising at least an outer layer of an electrocatalytically-active material which comprises an intimate mixture of ruthenium
5 oxide and at least one non-noble metal oxide which method comprises the step of depositing a mixture comprising the aforementioned oxides onto the substrate by physical vapour deposition.
2. A method as claimed in Claim 1 wherein the physical vapour deposition comprises radio frequency sputtering, sputter ion plating, arc evaporation, electron beam
10 evaporation, dc magnetron evaporation, or reactive physical vapour deposition.
3. A method as claimed in Claim 1 wherein the pressure in the deposition chamber in the PVD system is in the range of from 10^{-2} to 10^{-10} atmospheres.
4. A method as claimed in Claim 1 wherein the non-noble metal is tin.
5. A method as claimed in Claim 1 wherein the intimate mixture comprises ruthenium
15 oxide, a non-noble metal oxide and an oxide of a second noble metal.
6. A method as claimed in Claim 5 wherein the second noble metal is iridium.
7. A method as claimed in Claim 1 or 5 wherein the coating comprises at least 10 mole % of oxide of noble metal and at least 20 mole % of oxide of non-noble metal.
8. A method as claimed in Claim 6 wherein the coating comprises a mixture of RuO_2 ,
20 IrO_2 and SnO_2 .
9. A method as claimed in Claim 1 comprising a further step wherein the electrode prepared in the said step is heated to a high temperature for at least one hour.
10. An electrode which comprises a substrate of a valve metal or of an alloy thereof and a coating thereon comprising an outer layer of an electrocatalytically-active material
25 which comprises an intimate mixture of ruthenium oxide and at least one non-noble metal oxide wherein the outer layer is of substantially uniform thickness and wherein the contours thereof are at least substantially the same as the contours of the substrate immediately underlying it.
11. An electrode as claimed in Claim 10 wherein the oxidic component of the outer layer
30 provides more than 30 atomic % of all the components therein as measured by X-ray absorption spectroscopy.

12. An electrode which comprises a substrate of a valve metal or of an alloy thereof and a coating thereon comprising an outer layer of an electrocatalytically-active material which comprises an intimate mixture of ruthenium oxide and at least one non-noble metal oxide wherein the outer layer comprises small particles of a iridium/ruthenium intermetallic in a mixture of a poorly crystalline tin oxide/iridium oxide/ruthenium oxide mixture.

13. An electrolytic cell comprising an electrode as claimed in any one of Claims 10, 11 or 12.

14. A process for the preparation of chlorine using an electrolytic cell as claimed in Claim 13..




Fig.1.

INTERNATIONAL SEARCH REPORT

Intern. Application No

PCT/GB 94/01718

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C25B11/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C25B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 099 866 (ENERGY CONVERSION DEVICES, INC) 1 February 1984 see page 20, line 3 - page 21, line 3 see page 23, line 20 - line 24 see page 31, line 6 - line 10 ---	1-3, 9, 10
X	DE,A,26 25 820 (TDK ELECTRONICS CO. LTD) 30 December 1976 see page 5, line 14 - line 19 see page 9; claims 1-5,7 ---	1, 4, 5, 7 10, 12-14
A	US,A,4 696 731 (M. A. TENHOVER) 29 September 1987 see column 4, line 41 - line 46 see column 8 - column 9; claims 1, 13, 24, 25 -----	1, 2

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- * "A" document defining the general state of the art which is not considered to be of particular relevance
- * "E" earlier document but published on or after the international filing date
- * "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- * "O" document referring to an oral disclosure, use, exhibition or other means
- * "P" document published prior to the international filing date but later than the priority date claimed

- * "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- * "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- * "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- * "&" document member of the same patent family

Date of the actual completion of the international search

23 November 1994

Date of mailing of the international search report

12. 12. 94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Groseiller, P

INTERNATIONAL SEARCH REPORT

Information on patent family members

Interna

Application No

PCT/GB 94/01718

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0099866	01-02-84	US-A- 4537674 AU-B- 567500 AU-A- 1680083 CA-A- 1214452 JP-A- 59047390	27-08-85 26-11-87 26-01-84 25-11-86 17-03-84
DE-A-2625820	30-12-76	JP-C- 990070 JP-A- 51144381 JP-B- 53028279 GB-A- 1508091 US-A- 4061558	18-03-80 11-12-76 14-08-78 19-04-78 06-12-77
US-A-4696731	29-09-87	NONE	